



## 0.67 Noseeum Mesh

DATE: **8/5/2019**

		TEST METHOD
CONTENT:	<b>100% Nylon</b>	ASTM D629
WEIGHT (oz/sq yd):	<b>0.6 +/-12%</b>	ASTM D3776
WALES (width)/inch:	<b>32 +/-4</b>	ASTM D3887
COURSES (length)/ inch:	<b>39 +/- 5</b>	ASTM D3887
INSTRON BALL BURST (lbf):	<b>20 lbs Min</b>	ASTM D3787
MULLEN BURST:		ASTM D3786
THICKNESS (inch):	<b>0.0079 +/- 0.0009</b>	ASTM D1777
TENSILE (LENGTH)	<b>N/A</b>	ASTM D5034
(WIDTH)	<b>N/A</b>	ASTM D5034
ELONGATION (LENGTH)	<b>N/A</b>	ASTM D5034
(WIDTH)	<b>N/A</b>	ASTM D5034
COMMENTS	<b>0</b>	

REVISED DATE **5/21/2015**

SPECIFICATIONS ARE SUBJECT TO CHANGE WITHOUT NOTICE